

Technical Datasheet - Domed Fridge Magnets

Doming Resin

Composition: Aliphatic polyester urethane
Thickness: Approximately 1.5mm (\pm 0.5mm)

Matt White Magnetic Vinyl

Thickness: 850 micron (0.85mm)
Composition: Highest performing ferrite material with no plasticisers
Maximum Energy Product: 0.65 - 0.75 MGOe
Remanence: 1600 - 1900 G
Coercivity: 1200 - 1500 Oe
Intrinsic Coercivity: 2200 - 2500 Oe
Constant Working Temperature: -30°C to +80°C
Complies To: European Toy Safety Standard EN71 Part 3:1994 + A1:200
Reach Compliant: Yes